

Technical Datasheet – PU Polyester PPI80 (Black)

Properties	Test Method	Unit	Tolerance	Value
Density	ISO 845	kg/m ³	min./max	26 – 32
Plank thickness		mm	- 0 / + 10%	2 to 100
Plank width		mm	- 0 / + 30mm	1250
Plank length		mm	- 0 / + 50mm	2030
Compression load deflection	ISO 3386/1	kPa		3.2 – 5.2
Elongation at break	ISO 1798	%		230
Tensile Strength	ISO 1798	kPa		170
Cell count	CAL I 127.29	1/CM	min./max	18 - 21

